





Page 1 of 14 Pages

No.: RZUN2024-2078

检测报告 TEST REPORT

UN38.3

| NAME OF SAMPLE: | Lithium-ion battery pack | |
|-------------------------|--------------------------|--|
| 产品名称: | 锂离子电池组 | |
| | | |
| CLIENT: | EcoFlow Innovation Itd. | |
| 委托单位: | 深圳市正浩智造科技有限公司 | |
| | | |
| CLASSIFICATION OF TEST: | Commission Test | |
| 检测类别: | 委托测试 | |



检测报告

TEST REPORT

No.: RZUN2024-2078 Page 2 of 14 Pages

| | 1 ago 2 or 141 agos |
|--|---|
| Name of samples: Lithium-ion batterypack 样品名称:锂离子电池组 | Type/Model: 型号规格: EFD521-EB 51,2V 80Ah 4096Wh |
| Color: Black 样品颜色:黑色 | Physical shape:Prismatic 样品形状 : 棱柱形 |
| Commissioned by: EcoFlow Innovation Itd. 委托单位: 深圳市正浩智造科技有限公司 | Commissioner address:RM 101, Plant #1, Runheng Industrial Zone, Fuyuanyi Road, Zhancheng Community,Fuhai Street, Bao'an District,Shenzhen City,Guangdong Province, P.R.China 委托单位地址:深圳市宝安区福海街道展城社区福园一路润恒工业厂区 1#厂房 101 |
| Manufacturer: EcoFlow Innovation Itd. 制造商: 深圳市正浩智造科技有限公司 | Manufacturer address:RM 101, Plant #1, Runheng Industrial Zone, Fuyuanyi Road, Zhancheng Community,Fuhai Street, Bao'an District,Shenzhen City,Guangdong Province, P.R.China 制造商地址: 深圳市宝安区福海街道展城社区福园一路润恒工业厂区 1#厂房 101 |
| Factory: Zhuhai Pengyuan Energy Storage Technology Co.,Ltd. 生产厂: 珠海鹏远储能科技有限公司 | Factory address: Factory Building (1) ,Factory Building (2) , No.22 Chuangxing Middle Road, Hongqi Town, Jinwan District, Zhuhai, P. R.China. 生产厂地址: 珠海市金湾区红旗镇创兴中路 22 号厂房(一)、 厂房(二) |
| Classification of test: Commission Test 检测类别: 委托测试 | Quantity of sample: 4 battery packs, 30 cells 样品数量: 4 个电池组, 30 个电芯 |
| Tested according to: 测试标准: ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3 | Sample identification: 样品标识序号:b1#~b4#,c1#~c30# |
| Receiving date: 接样日期: 2024-03-11 | Means of receiving: Submitted by commissioner 接样方式。委托单位送样 |
| Completing date: 完成日期 : 2024-04-01 | Test item: 8 items 测试项目: 8 项 |
| Test conclusion: | |

Test conclusion:

检测结论:

The Lithium-ion battery packs submitted by EcoFlow Innovation Itd. are tested according to Section 38.3 of the Seventh revised edition Amendment 1 of the Manual of Tests and Criteria (ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3). The test items are full items. The test results comply with the relevant requirements of the standard.

由深圳市正浩智造科技有限公司送检的無离子电池组,依据联合国《试验和标准手册》第七修订版修正 1 第 38.3 节进行检测,试验为全项目,试验结果符合标准相关要求。
Seal of CVC

CV 盖章 Date of issue: 整歲期期2024-04-19

Title:Manager批准人职务:经理

Approved by: Huang Kun Reviewed by: Zhang Siyao Tested by: Deng Junzhao

批准: Hungken 审核: Zhang siyon 检测: Dang Junzhao

Description and illustration of the sample:

样品说明及描述:

The sample's status is good

样品状况良好。

The battery (EFD521-EB) is composed of cells (IFR40135), and the connection mode is:4P16S 电池组 (EFD521-EB) 由电芯 (IFR40135) 组成,连接方式为: 4P16S

Cell Dimensions/电芯尺寸: φ40mm*135mm

Watt-hour rating of each battery/ 单个电池组的瓦时率: 4096Wh

| Test item | Sample No. | State | Remark |
|-----------|------------|--|---|
| 试验项目 | 样品编号 | 状态 | 备注 |
| | b1#~b2# | at first cycle, in fully charged states 第一个交替充电放电周期完全充电状态 | - |
| T.1~T.5 | b3#~b4# | after 25 cycles ending in fully charged states 第 25 个交替充电放电周期完全充电状态 | - |
| T.6 | c1#~c5# | at first cycle at 50% of the design rated capacity 第一个交替充电放电周期充电到设计额定容量的 50% | |
| 1.0 | c6#~c10# | after 25 cycles ending at 50% of the design rated capacity 第 25 个交替充电放电周期充电到设计额 定容量的 50% | - |
| | b1#~b2# | at first cycle, in fully charged states 第一个交替充电放电周期完全充电状态 | using undamaged samples previously |
| T.7 | b3#~b4# | after 25 cycles ending in fully charged states 第 25 个交替充电放电周期完全充电状态 | used in tests T.1 to T.5 使用试验 T.1 至 T.5 未 损坏的样品 |
| | c11#~c20# | at first cycle, in fully discharged states 第一个交替充电放电周期完全放电状态 | - |
| T.8 | c21#~c30# | after 25 cycles ending in fully discharged states 第 25 个交替充电放电周期完全放电状态 | - |

The test objects of T.1~T.5 and T.7 are battery packs, and the sample numbers are b1#~b4# T.1~T.5、T.7 的测试对象为电池组,样品编号为 b1#~b4#。

The test objects of T.6 and T.8 are component cells, and the sample numbers are c1#~c30# T.6、T.8 的测试对象为组成电芯,样品编号为 c1#~c30#。

| Description of the sampling procedu | escription | tion of th | sampling | procedure |
|-------------------------------------|------------|------------|----------|-----------|
|-------------------------------------|------------|------------|----------|-----------|

取样程序的说明

/

Description of the deviation from the standard, if any:

试验结果不符合标准项的说明:

_/

Remarks:

备注:

Throughout this report a comma is used as the decimal separator.

本报告中以逗号代替小数点。


Ref. No.: RZUN2024-2078 Page 4 of 14 Pages

Photos of Samples and Labels/样品照片及标识

Battery/电池 (EFD521-EB 51,2V 80Ah 4096Wh)









Photos of Samples and Labels/样品照片及标识

Component Cell/内部电芯(IFR40135 3,2V 20Ah)





Ref. No.: RZUN2024-2078 Page 6 of 14 Pages

| ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3 | | | |
|---|--------------|--------|---------|
| Clause | Requirements | Result | Verdict |
| 章节 | 标准要求 | 测试结果 | 判定 |

| 38.3.4 | Procedure/试验步骤 | _ |
|----------|--|------------------|
| | Test T.1: Altitude simulation/试验 T.1: 高度模拟 | |
| 38.3.4.1 | Test cells and batteries shall be stored at a pressure of 11,6kPa or less for at lea six hours at ambient temperature (20±5℃)/ 将电芯和电池在温度为 20±5℃,大气力为不大于 11,6kpa 的环境中贮存不少于 6 个小时 | I |
| | Requirement/标准要求: 1 Cells and batteries Mass loss limit: ≤0,1% /样品质量损失≤0,1% 2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。 3 No leakage, no venting, no disassembly, no rupture and no fire 样品(电池)应无漏液、无排气、无线型以及无着火现象 The data is shown in Table 不数据见表 1 | id 羊 解 |
| 38.3.4.2 | Test T.2: Thermal test/试验 T.2: 温度试验 Test cells and batteries are to be stored for/电池存储条件如下: 1 For small cells and batteries: one temperature cycle: 72±2℃(6h) — 40±2℃(6h) For large cells and batteries: one temperature cycle: 72±2℃(12h) — 40±2℃(12h) The maximum time interval between test temperature extremes is 30 minutes/温转换最大间隔时间为 30min This procedure is to be repeated 10 times/重复 10 次循环 4 after which all test cells and batteries are to be stored for 24 hours at ambie temperature (20±5℃)/循环结束后,电池在 20±5℃的条件下 搁置 24 小时 Requirements/标准要求 1 Cells and batteries Mass loss limit: ≤0,1% /样品质量损失≤0,1% 2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后来看见证明的表面,是可能用的表面,可能用的表面,是可能用的表面,可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,是可能用的表面,可能 | g nt P |

Ref. No.: RZUN2024-2078 Page 7 of 14 Pages

| ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3 | | | |
|---|--------------|--------|---------|
| Clause | Requirements | Result | Verdict |
| 章节 | 标准要求 | 测试结果 | 判定 |

Test T.3: Vibration/试验 T.3: 振动

- 1 Cells and batteries are firmly secured to the platform of the vibration machine /电 芯和电池牢固地安装在振动台(的台面)上
- 2 The vibration: a sinusoidal waveform with a logarithmic sweep between 7Hz and 200Hz and back to 7Hz traversed in 15 minutes/振动以正弦波形式,以 7Hz 增加至 200Hz,然后在减少回到 7Hz 为一个循环,一个循环持续 15 分钟的对数前移传送。
- 3 For cells and small batteries: from 7 Hz a peak acceleration of 1gn is maintained until 18Hz is reached. The amplitude is then maintained at 0,8mm (1,6mm total excursion) and the frequency increased until a peak acceleration of $8g_n$ occurs (approximately 50Hz). A peak acceleration of $8g_n$ is then maintained until the frequency is increased to 200Hz. / 对于电芯和小型电池:从 7Hz 开始,以 1g_n 的峰值加速度保持不变,直到达到 18Hz。然后将振幅保持在 0,8mm(总偏移 1,6mm)并且频率增加直到出现 $8g_n$ 的峰值加速度(大约 50Hz)。然后保持 $8g_n$ 的峰值加速度,直到频率增加到 200Hz。

For large batteries: from 7Hz a peak acceleration of $1g_n$ is maintained until 18Hz is reached. The amplitude is then maintained at 0.8mm (1.6mm total excursion) and the frequency increased until a peak acceleration of $2g_n$ occurs (approximately 25Hz). A peak acceleration of $2g_n$ is then maintained until the frequency is increased to 200Hz. / 对于大型电池: 从 7Hz 开始,以 $1g_n$ 的峰值加速度保持不变,直到达到 18Hz。然后将振幅保持在 0.8mm(总偏移 1.6mm)并且频率增加直到出现 $2g_n$ 的峰值加速度(大约 25Hz)。然后保持 $2g_n$ 的峰值加速度,直到频率增加到 200Hz。

4 This cycle repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting position of the cell. One of the directions of vibration must be perpendicular to the terminal face. /以振动的其中一个方向必须是垂直样品极性,对每个电芯从三个互相垂直的方向上循环 12 次,每个方向 3 个小时,共 9 小时。

Requirements/标准要求

38.3.4.3

- 1 Cells and batteries Mass loss limit: ≤0,1% /样品质量损失≤0.1%
- 2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.

样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电芯。

 $3\,$ No leakage, no venting, no disassembly, no rupture and no fire

样品(电池)应无漏液、无排气、无解体、无破裂以及无着火现象的发生

The samples b1#~b4#:

No leakage, no venting, no disassembly, no rupture and no fire/编号为 b1#~b4#的样品: 无漏液、无排气、无解体、无破裂以及无着火现象

The data is shown in Table 1./数据见表 1

Р

| ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3 | | | |
|---|--------------|--------|---------|
| Clause | Requirements | Result | Verdict |
| 章节 | 标准要求 | 测试结果 | 判定 |

Test T.4: Shock/试验 T.4: 冲击

- 1 Test cells and batteries shall be secured to the testing machine/以稳固的托架固定住每个电芯和电池样品的全部配件表面。
- 2 Each cell shall be subjected to a half-sine shock of peak acceleration of 150 g_n and pulse duration of 6 milliseconds. Large cells may be subjected to a half-sine shock of peak acceleration of 50 g_n and pulse duration of 11 milliseconds. / 对每个电芯以峰值为 150 g_n 的半正弦的加速度撞击,脉冲持续 6 毫秒,大型电芯须经受最大加速度 $50g_n$ 和脉冲持续时间 11 毫秒的半正弦波冲击。

Small batteries shall be subjected to a half-sine shock of peak acceleration of 150 g_n

(or Acceleration(g_n)= $\sqrt{\frac{100850}{mass}}$, which is smaller) and pulse duration of 6

milliseconds, large batteries shall be subjected to a half-sine of peak acceleration of

50 g_n (or Acceleration(g_n)= $\sqrt{\left(\frac{30000}{mass}\right)}$, which is smaller) and pulse duration of 11

milliseconds/对每个电池以峰值为 $150g_n$ (或与 $\sqrt{\frac{100850}{mass}}$) 中的较小值)的半正弦的

38.3.4.4

加速度撞击,脉冲持续 6 毫秒,大型电池须经受最大加速度 $50g_n$ (或与 $\sqrt{\frac{30000}{mass}}$)中

的较小值)和脉冲持续时间 11 毫秒的半正弦波冲击。

3 Each cell or battery shall be subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks/每个电池或电池组须在三个互相垂直的电池安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受 18 次冲击。

Requirements/标准要求:

- 1 Cells and batteries Mass loss limit: ≤0,1% /样品质量损失≤0,1%
- 2 Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.

样品试验后开路电压应不低于试验前开路电压的 **90** %,此要求不适用于完全放完电的电池和电芯。

3 No leakage, no venting, no disassembly, no rupture and no fire

样品(电池)应无漏液、无排气、无解体、无破裂以及无着火现象的发生

The samples b1#~b4# : Acceleration= 30.1g_n

No leakage, no venting, no disassembly, no rupture and no fire/编号为 b1#~b4#的样

峰值加速度= 30.1gn

无漏液、无排气、无解体、无 破裂以及无着火现象

The data is shown in Table 1./数据见表 1

Р

Ref. No.: RZUN2024-2078 Page 9 of 14 Pages

| | ST/SG/AC.10/11/Rev.7/Amend.1/\$ | Section 38.3 | |
|--------------|---|---|---|
| Clause 章节 | Requirements Result 标准要求 测试结果 | | |
| | Test T.5: External Short Circuit/试验 T.5 外部短路 | | |
| | 1 The cell or battery to be tested shall be heated for reach a homogeneous stabilized temperature 57±4 稳定在 57±4℃ | | |
| 38.3.4.5 | 2 the cell or battery shall be subjected to a short circ resistance of less than 0,1 ohm at 57±4℃, This she for at least one hour after the cell or battery external to 57±4℃, or in the case of the large batteries, maximum temperature increase observed during the value. /将样品正负极用小于 0,1Ω 的总电阻回路进57±4℃之后保持短路状态 1 小时以上;对于大电池,半时实验结束。 | ort circuit condition is continued case temperature has returned has decreased by half of the ne test and remains below that 行短路,样品的外表温度恢复到 | P |
| 0.3.4.3 | 3 the cell or battery must be observed for a furth concluded, /对电芯或电池必须进一步观察 6 个小时才能下结论。 | er six hours for the test to be | F |
| | Requirements/标准要求: During the test and within six hours after test ,the cells or batteries 在试验过程中以及之后 6 个小时内,电芯或电池样品 1. External temperature not exceed 170℃ 外表温度不超过 170℃ 2. No disassembly, no rupture and no fire. 无解体、无破裂和无着火现象发生。 | The samples b1#~b4#: no disassembly, no rupture and no fire/编号为 b1#~b4#的 样品: 无解体、无破裂以及无 着火现象 The data is shown in Table 1./ 数据见表 1 | |

Ref. No.: RZUN2024-2078 Page 10 of 14 Pages

| | ST/SG/AC.10/11/Rev.7/Amend.1/Se | ection 38.3 | |
|--------|---------------------------------|-------------|---------|
| Clause | Requirements | Result | Verdict |
| 章节 | 标准要求 | 测试结果 | 判定 |

| 平月 | 你证安 不 | 例似名木 | TIVE . |
|----------|---|---|--------|
| | Test T.6: Impact / Crush / 试验 T.6: 撞击/挤压 | | Р |
| | Impact (applicable to cylindrical cells not less than 18 | mm in diameter) / | |
| | 撞击(适用于直径不小于 18 毫米的圆柱形电池) | | |
| | 1 This test sample cell or component cell is to be pla 试验样品用的电芯或聚合物电芯放在一个平坦光滑的平 | | |
| | 2 A 15,8 mm diameter bar is to be placed across the mass is to be dropped from a height of 61±2,5cm 15,8mm 的不锈钢圆棒横过电池中部放置后,将一质量的高度落向样品。 | onto the sample / 将一直径为 | |
| | 3 The test sample is to be impacted with its long surface and perpendicular to the longitudinal axis of curved surface lying across the centre of the test subjected to only a single impact./ 接受撞击的试样,放在试样中心的直径 15,8±0,1 毫米弯曲表面的纵轴;击。 | the 15,8 mm ± 0,1mm diameter sample. Each sample is to be 纵轴应与平坦的表面平行并与横 | Р |
| | Requirements/标准要求: | | |
| | 1 Cells external temperature not exceed 170℃.电 芯或电池的最高表面温度应不超过 170℃ 2 No disassembly, no fire within six hours of this test | The samples c1#~c10#: no disassembly and no fire/编号为 c1#~c10#的样品: 无解体、无着火现象 | |
| 38.3.4.6 | 试验结束后 6 个小时之内, 电芯和聚合物电芯应无解体和无着火现象发生 | The data is shown in Table 2./ 数据见表 2 | |
| | Crush (applicable to prismatic, pouch, coin/button cel 18mm in diameter) / 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小 | 于 18 毫米的圆柱形电池) | |
| | 1 A cell or component cell is to be crushed between is to be gradual with a speed of approximately 1,5 c The crushing is to be continued until the first of the th 将电池或元件电池放在两个平面之间挤压,挤压力度 速度大约为 1,5 厘米/秒。挤压持续进行,直到出现以下(a) The applied force reaches 13 kN ± 0,78 kN. / 施加(b) The voltage of the cell drops by at least 100 mV,/(c) The cell is deformed by 50% or more of its origin 度的 50%以上。 | m/s at the first point of contact. hree options below is reached. / 逐渐加大,在第一个接触点上的下三种情况之一: n的力达到 13kN±0,78kN 电池的电压下降至少 100 毫伏 hal thickness./电池变形达原始厚 | N/A |
| | 2. A prismatic or pouch cell shall be crushed by apply A button/coin cell shall be crushed by applying the cylindrical cells, the crush force shall be applied poaxis. /棱柱形或袋装电池应从最宽的一面施压。纽扎压。圆柱形应从与纵轴垂直的方向施压。 | force on its flat surfaces. For erpendicular to the longitudinal | N/A |
| | Requirements/标准要求: 1 Cells external temperature not exceed 170℃.电 | | |
| | 芯或电池的最高表面温度应不超过 170℃ | | |
| | 2 No disassembly, no fire within six hours of this test | - | |
| | 试验结束后 6 个小时之内,电芯和聚合物电芯应无解体和无着火现象发生 | | |

Ref. No.: RZUN2024-2078 Page 11 of 14 Pages

| ST/SG/AC.10/11/Rev.7/Amend.1/Section 38.3 | | | | |
|---|--|---|---------------|--|
| Clause 章节 | Requirements 标准要求 | Result 测试结果 | Verdict 判定 | |
| | Test T.7: Overcharge/试验 T.7: 过度充电 | | | |
| | 1 The charge current shall be twice the manufactucontinuous charge current/以 2 倍制造厂推荐的最大持2 The minimum voltage of the test shall be as follows | 续充电电流对样品充电 | | |
| 38.3.4.7 | a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V/ 如果厂家推荐的充电电压不超过 18V,本试验的最小充电电压应是厂家标定最大充电电压的两倍或者是22V之中的较小者。 b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1,2 times the maximum charge voltage/ 如果厂家推荐的充电电压超过 18V,本试验的最小充电电压应是厂家标定最大充电电压的 1,2倍。 3 Tests are to be conducted at ambient temperature 20±5℃, The duration of the test shall be 24 hours/20±5℃的环境温度下,试验持续 24 小时。 Requirements/标准要求: | The voltage of the test is 69.12V, and the current is 160A 试验的电压为 69.12V, 电流为 160A | P | |
| | No disassembly and no fire within seven days of this test 试验样品在试验中和试验后 7 天内,应无解体和无着火现象发生。 | 号为 b1#~b4#的样品: 无解体、无着火现象 For voltage data before test, see table 3. / 试验前电压见表 3 | | |
| | Test T.8: Forced discharge/试验 T.8: 强制放电 | | | |
| | Each cell shall be forced discharged at ambient temporal series with a 12 V D.C. power supply at an initial currence discharge current specified by the manufacturer, 20±5℃的环境温度下,将单个电芯连接在 12V 的直流 | ent equal to the maximum | | |
| | 电源提供给每个电芯初始电流为制造厂指定的最大放电电流。 | | | |
| 38.3.4.8 | The specified discharge current is to be obtained by one the appropriate size and rating in series with the test discharged for a time interval (in hours) equal to its ratinitial test current (in ampere) | cell. Each cell shall be forced | P | |
| | 指定的放电电流通过串联在试验电芯上的合适大小和: 强制放电时间(小时)为额定容量除以初始电流(安培 | | | |
| | Requirements/标准要求: | The samples c11#~c30#: | | |
| | No disassembly and no fire within seven days of this test 试验样品在试验中和试验后 7 天内,应无解体和无着火现象发生。 | no disassembly and no fire/编号为 c11#~c30#的样品: 无解体、无着火现象 The data is shown in Table 4./数据见表 4 | | |

| ω |
|-----------|
|)78 |
| 0 |
| -201 |
| |
| 24 |
| 0 |
| ∾ |
| UN20 |
| \supset |
| RZ |
| 깥 |
| |
| ď |
| ĭ |
| 2 |
| Ť. |
| 윤 |
| മ |

| | Test T.5: External Short Circuit 试验 T.5 外部 短路 | Temp. (°C) 温度 (°C) | 57,0 | 57,1 | 56,9 | 57,1 |
|--------------------------------|---|--|--------|--------|--------|--------|
| | Test T.4: Shock/ 试验 T.4: 冲击 | OCV Retention Ratio(%) 电压保留比 (%) | 100,00 | 100,00 | 100,00 | 100,00 |
| Table1: T1~T5 / 表 1. 试验 1~试验 5 | | Mass Loss(%) 质量损失(%) | 0,000 | 0,000 | 0,000 | 0,000 |
| | Test T.3: Vibration/ 试验 T.3: 振动 | OCV Retention Ratio(%) 电压保留比 (%) | 100,00 | 100,00 | 100,00 | 100,00 |
| | | Mass Loss(%) 质量损失(%) | 0,000 | 0,000 | 0,000 | 0,000 |
| | Test T.2: Thermal test/ 试验 T.2: 温度试验 | OCV Retention Ratio(%) 电压保留比 (%) | 99,91 | 99,91 | 99,92 | 66,95 |
| | | Mass Loss(%) 质量损失(%) | 0,000 | 0,000 | 0,000 | 0,000 |
| | Test T.1: Altitude simulation/ 试验 T.1: 高度模拟 | OCV Retention Ratio(%) 电压保留比 (%) | 100,00 | 100,00 | 100,00 | 100,00 |
| | | Mass Loss(%) 质量损失(%) | 0,000 | 0,000 | 0,000 | 0,000 |
| | ocv prior to test /试 验前电 压(V) | | 53,298 | 53,271 | 53,312 | 53,288 |
| | Mass prior to test / 试 最前质 量(kg) | | 33,10 | 33,15 | 33,04 | 33,19 |
| | Sample No. | 样品号 | b1# | p2# | p3# | p4# |

| Table2: Impact / 表 2: 撞击 | t c2# c3# c4# c5# c6# c7# c8# c9# c10# | 3 3,297 3,297 3,292 3,290 3,291 3,292 3,295 3,295 | 2 23,1 23,0 23,1 23,0 23,2 23,0 23,1 23,0 23,2 | | |
|--------------------------|--|---|--|--|--|
| Table2: Impact / 3 | | 3,295 | | | |
| | c1# c2# | | 23,2 23,1 | | |
| | Sample No. 样品号 | OCV prior to test / 试验前电压(V) | Temp. (℃) 温度 (℃) | | |
| | Test T.6: Impact/试验 T.6: 撞击 | | | | |

| | Table3: Overcharge T | Test of batteries/ | eries/表3 | 表3过度充电 | | |
|--------------|----------------------|--------------------|----------|--------|--------|---|
| Test T.7: | Sample No. | 17 | #01 | #64 | 777 | _ |
| Overcharge / | 样品号 | #10 | #Z0 | D2# | D4# | |
| 试验 1.7: 过度 | OCV prior to test | 010 01 | 100 02 | 020 03 | 20 044 | _ |
| 充电 | /试验前电压(V) | 23,230 | 52,774 | 53,270 | 55,244 | |

| Page 13 of 14 Pages | | #. | 91 | #. | 06 |
|-------------------------|---------------------------------------|-------------------|---------------------------------|--------------------|---------------------------------|
| 3 13 of | | c20# | 2,691 | c30# | 2,690 |
| Page | | c19# | 2,689 | c29# | 2,692 |
| | | c18# | 2,692 | c28# | 2,688 |
| | | c17# | 2,692 | c27# | 2,687 |
| | 放电 | c16# | 2,697 | c26# | 2,682 |
| | Table 4: Forced discharge / 表 4. 强制放电 | c15# | 2,695 | c25# | 2,691 |
| | | c14# | 2,697 | c24# | 2,690 |
| | | c13# | 2,692 | c23# | 2,689 |
| | | c12# | 2,686 | #270 | 2,687 |
| | | c11# | 2,697 | c21# | 2,691 |
| Ref. No.: RZUN2024-2078 | | Sample No. 样品号 | OCV prior to test / 试验前电压(V) | Sample No. 样品号 | OCV prior to test / 试验前电压(V) |
| Ref. No.: RZ | | i i | Forced discharge / | 以数 T.8: 品 整 产 品 | |

后个

Ref. No.: RZUN2024-2078 Page 14 of 14 Pages

注意事项 Important

1. 报告无检测单位印章无效。

The test report is invalid without the seal of CVC.

2. 未经本试验室书面同意,不得部分地复制本报告。

Nobody is allowed to photocopy or partly photocopy this test report without written permission of CVC.

3. 本报告无批准人、审核人及检测人签名无效。

The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.

4. 本报告涂改无效。

The test report is invalid if altered,

- 5. 对检测报告若有异议,应于收到报告之日起十五天内向检测单位提出。 Objections to the test report must be submitted to CVC within 15 days.
- 6. 本报告仅对送检样品负责。

The test report is valid for the tested samples only.

7. 判定栏中"-"表示"不需要判定","P"表示"通过","F"表示"不通过", "N/A"表示"不适用"。

As for the Verdict, "-" means "no need for judgement", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

报告中未加 CMA 标志时,检测数据和结果仅供科研、教学或内部质量控制之用。
The test data and test results given in this test report should only be used for purposes of scientific research, teaching and internal quality control when the CMA symbol is not presented.

地 址: 广东省广州市科学城开泰大道天泰一路3号

广东省广州市黄埔区光谱东路 179 号百事高智慧园 D 栋 (测试地点)

Lab Address: No.3, Tiantai 1st Road, Kaitai Avenue, Science City, Guangzhou, Guangdong, China. Testing Location: Building D, BASIGO INTELLIGENT, No.179, Guangpu East Road, Huangpu District, Guangzhou, P. R. China.

http://www.cvc.org.cn